

September 6, 2017

HIRAOKA

HG SERIES Enhanced BLOCK-OUT

Physical Properties

Test Items	HG102(BP)	HG212(BP)	HG313(BP)	Unit	Test Method
Width	2040	2040	2040	mm	ASTM D 751
	80.3	80.3	80.3	inch	
Total Mass	1000	1130	1280	g/m ²	ASTM D 751
	29.5	33.3	37.8	oz/yd ²	
Thickness	0.77	0.88	1.02	mm	ASTM D 751
	30.3	34.6	40.2	mil.	
Tensile Strength (Cut Strip) Warp Fill	3100	5100	6100	N/5cm	ASTM D 751
	2800	5200	5900		
	354	582	697	lbs/inch	
	320	594	674		
Tear Strength (Trapezoid) Warp Fill	160	400	670	N	ASTM D 751
	160	400	670		
	36	90	151	lbs	
	36	90	151		
Tear Strength (Trapezoid) Warp Fill	300	630	1100	N	DIN 53363
	300	630	1000		
Adhesion	100	130	140	N/5cm	ASTM D 751
	11	15	16	lbs/inch	
Light Transmisson	0	0	0	%	ISO 9050
Temperature Resistance	-40 / +70	-40 / +70	-40 / +70	°C	ASTM D2136 MSAJ/M-03-2003
	-40 / +158	-40 / +158	-40 / +158	°F	
Flame Retardancy	B-s2,d0	B-s2,d0	B-s2,d0	EN13501-1	
	meet	meet	meet	NFPA-701	
	meet	meet	meet	ASTM E-84	

The above data reflects average measured values.